### 😥 Cranberry°

### 

Go beyond with our Patented Low Dermatitis Technology that reduces the risk of skin hypersensitivity. Experience a purer nitrile with superior tensile strength that outperforms traditional nitrile gloves

Free of Sulfur-based Chemical Accelerators Ultimate Durability
Superior Tensile Strength

# BEYOND PROTECTION

Protect against Type I & Type IV Hypersensitivity

Excellent Tactile Sensitivity

Cronberru

M

TRANSCANE

#### Tensile Strength Comparison Chart

Physical Properties	Stardard*	Transcend	
Tensile Strength (MPa) unaged	21-25	26-34	N
Tensile Strength (MPa) aged	21-30	31-37	-

comparison to nitrile gloves with similar specifications

# TRANSCIND<sup>™</sup> nitrile powder free exam gloves

Features	Benefits
Patented Low Derma Technology	No chemical accelerators are added during the manufacturing process, reducing the risk of skin dermatitis
Superior Tensile Strength	Exceptionally strong and flexible formulation that prevents tearing, especially while donning
Anti-Slip Grip	Provides secure handling in wet and dry conditions ${\mathbb R}$ $ullet$
300 Space Saver Pack	Maximize storage space and efficiency

Recommended for use by:

i) Individuals with sensitive skin who are looking for a purer nitrile alternative.

ii) Individuals seeking a soft and tear-resistant protective solution with excellent grip.

iii) Individuals who would like to save space and reduce packaging waste.

Product Specification & Typical Performance (ASTM D6319 & EN 455)						
	ASTM D6319	Transcend		ASTM D6319	Transcend	
Thickness (mm)			Physical Properties - unaged			
~ Finger	Min. 0.08	0.12-0.13	~ Tensile Stre ngth (MPa)	Min. 14	26-34	
~ Palm	Min. 0.06	0.07-0.08	~ Elongation (%)	500	540-580	
~ Cuff	Min. 0.05	0.06-0.07	~ Force at Break (N)	Min. 6.0	7.3-8.3	
Dimension (mm)			Physical Properties - aged			
~ Length 🕽	Min. 240	244-246	~Tensile Strength (MPa)	Min. 14	31-37	
~ Width ↔	XS (76±4) S (86±4) M (95±4) L (106±4) XL (115±4)		~ Elongation (%)	400	560-580	
			~ Force at Break (N)	Min. 6.0	8.5-9.3	

Single Use Only, Ambidextrous, Non-Sterile

Packaging: 300 gloves/box, 10 boxes/case, \*XL: 250 gloves/box

**XS** (3365) **M** (3367) **XL\*** (3369)

**S** (3366) **L** (3368)



## 🖸 Cranberry®

 Cronberry

 TRONSCINC

 Image: Construction Construct



### Nitrile Powder Free Examination Gloves

- Protection against accidental exposure
- No chemical accelerators added, reducing risk of skin dermatitis
- Anti-Slip grip for secure handling in all conditions
- 300 Space Saver pack to maxmize storage space and efficiency
- Fingertip textured in Matte Blue

Recommended for use by:

i) Individuals with sensitive skin who are looking for a purer nitrile alternative.

- ii) Individuals seeking a soft and tear-resistant protective solution with excellent grip.
- iii) Individuals who would like to save space and reduce packaging waste.

\*250/bx

Product Information								
Material	Nitrile		Finger Thickness	0.13 mm / 2.7 mil				
Color	Matte Blue		Palm Thickness	0.08 mm / 2.5 mil				
Length (mm)	244 - 246		Cuff Thickness	0.07 mm / 2.4 mil				
Texture	Fingertip		Powder Content	Powder-Free				
Sterile	No		Tensile Strength	26 - 34 MPa				
Product Sizing								
Palm Width (mm)	XS (CR3365)	Small (CR3366)	Medium (CR3367)	Large (CR3368)	XL (CR3369)			
	76 ± 4	86 ± 4	95 ± 4	106 ± 4	115 ± 4			

#### Product Compliance

ASTM D6319 & EN455 Nitrile Examination Gloves for Medical Application ASTM D6978 Resistance of Medical Gloves to Permeation by Chemotherapy Drugs FDA Title 21 CFR 177.2600 Food Contact and rubber articles intended for repeated use EN 16523-1 Determination of material resistance to permeation by chemicals EN 374-4 Protective Gloves Against Chemicals and Micro-organisms ISO 10993-10 Dermal Sensitization Assay & Primary Skin Irritation

Ecological Information

Bio-Compatibility: The chemical formulation of the gloves and surface lubricating materials do not contain any substances normally known to be harmful to the user or to any person with whom the gloves contact.

Other information

To prolong product life, gloves should be stored in a cool, dry location, located away from heat and light.